

COPY LIFE

Carta a superficie naturale, fabbricata con l'85% di cellulosa riciclata post-consumer disinchiostata e sbiancata T.C.F. ed il 15% di cellulosa E.C.F. di legno proveniente da boschi, i cui responsabili attuano i principi e le misure per garantire una gestione sostenibile delle foreste. FSC MIXED CoC 000010

Il prodotto è Acid Free, con riserva alcalina.

Alto grado di bianco. Idonea per fotocopie, stampa laser, ink-jet e fax a carta naturale.

Uncoated paper, made with 85% of post-consumer recycled pulp de-inked and bleached T.C.F. and 15% of bleached pulp E.C.F. manufactured from trees, whose producers comply with methods and policy to guarantee a sustainable management of forest. FSC MIX CoC 000010

The product is Acid Free, with alkaline reserve.

High grade of white. Suitable for photocopies, laser printing, ink-jet and faxing.

CARATTERISTICHE - PROPERTIES	METODOLOGIA - METHOD	U.M.	TARGET	Min.	Max.
Umidità Assoluta Moisture Content	UNI EN 20287 E.d.P.	%		4,0	5,0
Grammatura Gramaqe	UNI EN ISO 536 I.O. 10 P44 004	g/m ²	80,0	78,0	82,0
Spessore Thickness	UNI EN 20534 I.O. 10 P44 005	microns		100,0	108,0
Assorbimento acqua [Cobb] Water absorptiveness [Cobb]	UNI EN 20535 I.O. 10 P44 010	g/m ²			30,0
Grado di Bianco Brightness	UNI 7623 I.O. 10 P44 006	%	105,5	104,0	107,0
C.I.E. Whiteness C.I.E. Whiteness	ISO 11475 I.O. 10 P44 006		150,0	147,0	153,0
Opacità Opacity	UNI 7624 I.O. 10 P44 006	%		91,0	
Ruvidità [Bendtsen] Roughness [Bendtsen]	UNI 7626-2 I.O. 10 P44 007	ml/1'		200,0	300,0